

Rheological Additive for Moderate to High Polarity Organic Systems

GENERAL INFORMATION

BENTONE 27 rheological additive is an organic derivative of a hectorite clay. It is designed for moderate to high-polarity organic systems and for synthetic binders.

PHYSICAL PROPERTIES

Composition	organic derivative of a hectorite clay
Color / Form	creamy white, finely divided powder
Density	1.8 g/cm ³
Moisture	max 3.0 %

APPLICATIONS

- Adhesives and mastic compounds
- Anti-corrosive paints
- Anti fouling paints
- Cosmetics
- Foundry mould paints
- Gravure and flexographic printing inks
- Industrial finishes
- Plastisols, organosols
- Wash primers

KEY PROPERTIES

BENTONE 27 rheological additive

- increases viscosity
- provides thixotropy
- prevents pigment settling during storage
- improves flow and leveling
- controls sagging on vertical surfaces and penetration on porous substrates
- prevents syneresis in thixotropic systems

INCORPORATION

General

Incorporation of BENTONE 27 in organic systems (e.g. paints) requires high-shear dispersion equipment and a chemical activator.

Two basic incorporation methods can be used:

1. Addition of BENTONE 27 as a dry powder for in-situ dispersion and activation

The BENTONE 27 powder is added directly to the resin/solvent blend and is thoroughly mixed for 10 minutes. A chemical activator (see below) should be added next and mixed for 10 minutes. The pigments and fillers are then added and dispersed with high shear for at least 15 minutes.

2. Addition of BENTONE 27 as pregel of 5%–10% by weight

The solvent is charged to the mixing tank. BENTONE 27 powder is added and dispersed under high shear. A chemical activator can then be introduced to optimize gelation (see below).

For incorporation in the full formulation the pregel is added to the resin/solvent mixture with stirring. Pigments and fillers are then incorporated and dispersed under high shear.

For more details see Rheology Handbook.

Suitable dispersion equipment

High-speed disc impellers (Cowles dissolver); Ultra-Turrax, pearl-, sand-, ball- and three-roll mills.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

Chemical activators

Recommended to ensure full activation, i.e. optimum efficiency of BENTONE 27.

Suitable chemical activator	% based on weight of dry BENTONE 27
Methanol/H ₂ O (95/5)	33 %
Propylene carbonate	33 %
Propylene carbonate/ H ₂ O (95/5)	33 %
Ethanol/ H ₂ O (95/5)	50 %
Acetone/ H ₂ O (95/5)	60 %

LEVELS OF USE

The level depends on the system in which BENTONE 27 is to be used.

In paints of intermediate or high polarity, typical levels range between 0.2 and 1.0% BENTONE 27 (dry) based on total system weight. In synthetic resins (epoxy, polyester), quantities to be added are between 0.5 and 1.0 %.

HANDLING AND SAFETY

More detailed information on handling and safety for each product is included in the relevant material safety data sheet, available for each product.

STORAGE RECOMMENDATIONS

Store in a cool, dry location.

PACKAGING

BENTONE 27 rheological additive is available in multi-ply paper bags. Please contact your local Elementis Specialties representative for the packaging available in your region.

SHELF LIFE

BENTONE 27 has a shelf life of 4 (four) years from date of manufacture.

PRODUCT NUMBER

10791

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

USA Head Office

Elementis Specialties, Inc.
P.O. Box 700
329 Wyckoffs Mill Road
Hightstown, NJ 08520 USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis Service Centre NV
De Kleetlaan 12A, P.O. Box 3
1931 Diegem, Belgium
Tel.: +32 2 790 76 00
Fax: +32 2 790 76 60

Asia

Elementis Specialties, Inc.
120 Jalan Kapar 27/89
40400 Shah Alam
Malaysia
Tel.: +60 3 5192 2887
Fax: +60 3 5192 3887

Japan

Elementis Japan KK
15-14 Minaminisemba 1-Chome
Chou-Ku, Osaka
542-0081 Japan
Tel.: +81 6 6267 6211
Fax: +81 6 6267 6215